Ultracell®

'Quality in Every Language'

UL1.3-12

12V 1.3Ah

General Series



Technical Dimensions (mm)







Ultracell
'Quality in Every Language'

Ultracell (UK) Ltd | Vesty Business Park, Vesty Road, Liverpool, L30 1NY, United Kingdom
Tel: +44 (0) 151 523 2777 | Fax: +44 (0) 151 523 0855 | Email: info@ultracell.co.uk
www.ultracell.co.uk

UL-V1-REV1 11/19
ALL DATA IS SUBJECT TO CHANGE WITHOUT NOTICE

Ultracell®
'Quality in Every Language'

TechData

UL1.3-12
12V 1.3Ah
General Series

Image

Terminal Dimensions (mm)

Standard
Terminal: F1



Technical Specification

Output	Nominal Voltage Nominal Capacity (20HR)	12V 1.3Ah
Terminal Type	Standard Terminal	F1
Container Material	Standard Option Flame Retardant Option (FR)	ABS ABS (UL94:VO)
Rated Capacity	(20HR 1.80V/cell, 25°C) (10HR 1.80V/cell, 25°C) (5HR 1.75V/cell, 25°C) (3HR 1.75V/cell, 25°C) (1HR 1.60V/cell, 25°C)	1.30 Ah/0.065A 1.12 Ah/0.112A 1.01 Ah/0.202A 0.882 Ah/0.294A 0.728 Ah/0.728A
Max Discharge Current	18A (5s)	
Internal Resistance	Approx 90.0mΩ	
Discharge Characteristics	Operating Temp Range	Discharge: -15 ~ 50°C Charge: 0 ~ 40°C Storage: -15 ~ 40°C
	Nominal Operating Temp Range	25 ± 3°C
	Cycle Use	Initial Charging Current less than 0.36A. Voltage 14.4V ~ 15.0V @ 25°C Temp. Coefficient -30mV/°C
	Standby Use	No limit on initial charging current. Voltage 13.5V ~ 13.8V @ 25°C Temp. Coefficient -20mV/°C
	Capacity affected by Temperature	40°C 103% 25°C 100% 0°C 86%
Design Floating Life at 20°C	5 Years	

Self Discharge

Ultracell® UL batteries may be stored for up to 6 months at 25°C and then a refresh charge is required. For higher temperatures the time intervals will be shorter.

Constant Current Discharge / Constant Power Discharge At 25°C (Amperes & Watts/Cell)

A = Amperes W = Watts

F.V/TIME A / W	5 min	10 min	15 min	20 min	30 min	45 min	60 min	2 hours	3 hours	4 hours	5 hours	6 hours	8 hours	10 hours	20 hours
1.85V/cell	2.30 4.35	1.61 3.06	1.32 2.55	1.15 2.23	0.922 1.80	0.709 1.39	0.580 1.14	0.354 0.701	0.270 0.536	0.222 0.442	0.188 0.377	0.163 0.327	0.130 0.261	0.108 0.217	0.064 0.120
1.80V/cell	2.83 5.28	1.92 3.61	1.54 2.93	1.30 2.50	1.02 1.98	0.773 1.51	0.624 1.22	0.376 0.741	0.284 0.560	0.233 0.462	0.196 0.390	0.170 0.339	0.134 0.269	0.112 0.224	0.065 0.121
1.75V/cell	3.36 6.18	2.17 4.05	1.69 3.20	1.41 2.70	1.09 2.10	0.821 1.59	0.656 1.28	0.392 0.768	0.294 0.577	0.240 0.474	0.202 0.399	0.174 0.345	0.138 0.274	0.114 0.226	0.066 0.121
1.70V/cell	3.81 6.93	2.39 4.42	1.83 3.43	1.52 2.88	1.14 2.19	0.853 1.64	0.684 1.33	0.409 0.796	0.303 0.592	0.246 0.483	0.207 0.406	0.179 0.352	0.140 0.277	0.116 0.229	0.067 0.122
1.65V/cell	4.20 7.54	2.57 4.69	1.94 3.59	1.59 2.99	1.19 2.26	0.886 1.70	0.713 1.37	0.421 0.814	0.311 0.604	0.251 0.490	0.211 0.413	0.182 0.357	0.142 0.280	0.117 0.231	0.068 0.124
1.60V/cell	4.41 7.79	2.68 4.82	2.02 3.70	1.65 3.05	1.23 2.30	0.906 1.72	0.728 1.39	0.434 0.834	0.318 0.615	0.258 0.499	0.216 0.419	0.186 0.362	0.145 0.284	0.119 0.234	0.069 0.124

VdS
MH 29410
CE 1188
ISO9001 CERTIFIED

Ultracell (UK) Ltd | Vesty Business Park, Vesty Road, Liverpool, L30 1NY, United Kingdom
Tel: +44 (0) 151 523 2777 | Fax: +44 (0) 151 523 0855 | Email: info@ultracell.co.uk
www.ultracell.co.uk

UL-V1-REV1 11/19
ALL DATA IS SUBJECT TO CHANGE WITHOUT NOTICE

Ultracell®
'Quality in Every Language'

TechData

UL1.3-12
12V 1.3Ah
General Series

Discharge Characteristics



Float Charging Characteristics



Temperature Effects in Relation to Battery Capacity



Effects of Temperature on Long Term Float Life



Cycle Life in Relation to Depth of Discharge



General Relation of Capacity vs. Storage Time



General Relation of Capacity vs. Storage Time (Notes)

A) No supplementary charge required.
(Carryout supplementary charge before use if 100% capacity is required.)

B) Supplementary charge required before use. Optional charging way as below:
1. Charged for above 3 days at limited current 0.25CA and constant voltage 2.25V/cell.
2. Charged for above 20 hours at limited current 0.25CA and constant voltage 2.25Vcell.
3. Charged for 8 ~ 10 hours at limited current 0.05 CA.

C) Supplementary charge may often fail to recover the capacity.
The battery should never be left standing till this is reached.

MH 29410

CE 1188

ISO9001 CERTIFIED

Ultracell (UK) Ltd | Vesty Business Park, Vesty Road, Liverpool, L30 1NY, United Kingdom
Tel: +44 (0) 151 523 2777 | Fax: +44 (0) 151 523 0855 | Email: info@ultracell.co.uk
www.ultracell.co.uk

UL-V1-REV1 11/19
ALL DATA IS SUBJECT TO CHANGE WITHOUT NOTICE